

Capital Tape Co, Inc
4920 Commerce Parkway #11
Cleveland, OH 44128
Fax: 887-893-3337



VK2526 STRUCTURAL GLAZING SPACER

Spacer for curtain wall structural silicone applications.

PHYSICAL PROPERTIES:

Density (lbs./cubic foot)		25
Hardness (Shore A)	ASTM D2240	40
Tensile Strength	ASTM D412	175 psi
Elongation	ASTM D412	70%
Compression Deflection @ 25%	ASTM D1667	26 psi
Compression Set @ 25%	ASTM D1667	10
Water Absorption (% by volume)	GTP*	1.2
Dynamic Shear	GTP*	55 psi
Dynamic Tensile	GTP*	65 psi
Thermal Conductivity	ASTM C518	0.33
Recommended Service Temperature		-10°F to 180°F -23°C to 100°C
Recommended Application Temperature		50°F to 110°F 10°C to 45°C
Fungi resistance	Good	
Oxidation resistance	Good	
Weather resistance	Good	

*GTP – Gaska Tape Test Procedure

These are approximate values and do not constitute warranty that products are fit for a particular purpose. The customer is advised to fully determine the suitability of these products for his intended use. These products conform to published specifications, if any, and the products are merchantable. Test data contained herein is believed to be reliable but unless specifically stated are not to be taken as specifications for products.