Capital Tape Co, Inc 4920 Commerce Parkway #11 Cleveland, OH 44128 Fax: 216.292.3435



## **V1510 Medium Density PVC Foam**

Aggressive, pressure-sensitive adhesive on one side of a medium density, closed cell foam. These tapes provide an excellent combination of flexibility and conformability with strength and wear resistance. Performs in tough applications where a tape must still flex to fit and seal. Excellent dimensional stability and a cushion against heavier loads. This foams density allows for clean die cuts and fastener penetration. Withstands wear and abrasion.

## Physical properties:

Weather resistance

Density	ASTM D-1667		15 lbs./cu.ft.
Hardness (Shore 00)	ASTM D-2240		40
Force to Compress (@ 25%)	ASTM D-1667		7 psi 48 kPa
Compression Set 25% (% loss from original height)	ASTM D-1667		8%
Peel Adhesion	ASTM D-1000		3-4 lbs.
Water absorption (% by volume)	GTP		1.0
Tensile Strength	ASTM D-412		80 psi 550 kPa
Percent Elongation	ASTM D-412		160
Thermal Conductivity (K factor) (btu-in.)/(hr.,sq.ft.)(F°)	ASTM C-518 w.mK		0.30
Recommended Service Temperature 12 month shelf life		-30°F to 200°F -35°C to 90°C	
Recommended Application Temperature		50°F to 110°F 10°C to 45°C	
Fire Rating		Meets or exceeds FMVSS 302A Self-Extinguishing/No Burn Rate	
Fungi resistance Excelle Oxidation resistance Excelle			

The values stated in charts are averages and are not to be construed as a warranty. Products must be tested by the end user for suitability in their applications. Made in USA.

Excellent